

# Rhinomould

## Product Data Sheet

Appearance:	Off white powder
Package:	40 kg paper bags also in 1 ton bulk bag
Contents:	Calcium Sulphate hemihydrate
Purity:	$\text{CaSO}_4 \frac{1}{2}\text{H}_2\text{O}$ 92-96%
Packing density:	0,6 - 0,8 g.cm <sup>3</sup>
Specific gravity:	2,6
Phl:	4,0 - 7,0 units
Total combined moisture:	5,0 - 7,0%
Setting time:	CN: 10 - 30 minutes VN: 60 - 100 minutes
Water demand:	85 - 95ml/100g plaster
Specific surface:	7 000 - 10 000 cm <sup>2</sup> /g
Compressive strength:	4 - 6 N/mm <sup>2</sup>
Mix volumes: At 90ml/100g.	90ml
Dry set density: At 90ml/100g	0,95g/ml
Reflectance:	.90,2%



**Saint-Gobain Construction Products South Africa (Pty) Ltd**

1 Shale Rd, NI Business Park (intersection of Old Johannesburg Road and Tlokwá Street), Kosmosdaal, Centurion South Africa

**Technical enquires:**  
If technical assistance is required, please contact Gyproc Customer Service Centre  
**Telephone:** 0860 272 829  
**Email:** ZA.Enquiries@saint-gobain.com  
**www.gyproc.co.za**

Saint-Gobain Construction Products South Africa (Pty) Ltd (SGCPSA) is a limited liability company registered in South Africa under company registration number 1937/010220/07.

SGCPSA reserves the right to revise product specification without notice.

The information herein should not be read in isolation as it is meant only as guidance for the user, who should always ensure that they are fully conversant with the products and systems being used and their subsequent installation prior to the commencement of work. For a comprehensive and up-to-date library of information visit the Gyproc SA website at: [gyproc.co.za](http://gyproc.co.za).

